

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 303 (1989): Plywood for General Purposes - [CED 20: Wood and other Lignocellulosic products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard

**PLYWOOD FOR GENERAL PURPOSES —
SPECIFICATION**

(Third Revision)

भारतीय मानक

सामान्य प्रयोजनों के लिए प्लाईवुड — विशिष्ट

(तीसरा पुनरीक्षण)

(First Reprint JUNE 1994)

UDC 676-419-32

© BIS 1990

**BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002**

FOREWORD

This Indian Standard (Third Revision) was adopted by the Bureau of Indian Standards on 21 December 1989, after the draft finalized by the Wood Products Sectional Committee had been approved by the Civil Engineering Division Council.

Indian Standard Specification for commercial (common) and moisture proof plywood (tentative) (IS 303 : 1951) published in 1951. This was subsequently revised in 1960 and 1975. This is the third revision of the standard and in this revision, care has been taken to utilize the depleting wood resource judiciously.

In the second revision of the standard, namely, IS 303 : 1975 provided for four grades of plywood based on the type of adhesive used and ten types of plywood depending upon the visual features of face and back thus making a total of as many as 40 classes of plywood.

In this revision, BWR and CWR grades are deleted and the WWR is replaced by moisture resistant or MR grade with temperature of water under normal atmospheric pressure in which test piece shall be immersed brought down to $60 \pm 2^\circ\text{C}$ from $70 \pm 2^\circ\text{C}$. This revision deletes face 'A' and 'D' quality of plywood, and retains face 'B' and 'C' now renamed as 'A' and 'B' thereby permitting in all 3 types of plywood based on appearance.

In the formulation of this standard, due weightage has been given to international coordination among standards and practices prevailing in different countries in addition to relating it to practices in the field in this country.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified in this standard.

Indian Standard

PLYWOOD FOR GENERAL PURPOSES — SPECIFICATION

(*Third Revision*)

1 SCOPE

1.1 This standard covers the requirements of different grades and types of plywood used for general purposes.

2 REFERENCE

2.1 The Indian Standards listed in Annex A are necessary adjuncts to this standard.

3 TERMINOLOGY

3.0 For purpose of this standard, the definitions given in IS 707 : 1976 shall apply.

4 GRADES

4.1 Plywood for general purposes shall be of the following two grades, depending upon the bond strength developed by the adhesive used for bonding the veneers:

- a) Boiling water resistant or BWR Grade, and
- b) Moisture resistant or MR Grade.

4.1.1 These shall be manufactured in accordance with 6.1 and 6.2. The grades shall conform to the general requirements given in 7 and the test requirements laid down in 11.

5 TYPES BASED ON CLASSIFICATION BY APPEARANCE

5.1 Plywood for general purposes shall be classified into three types, namely, AA, AB and BB based on the quality of the two surfaces, namely, A and B in terms of general permissible defects. The type of plywood shall, therefore, be designated by the kind of surfaces of the panels. The better quality surface shall be called 'face', and the opposite side shall be called 'back'. If the face and the back are of the same quality, they are not distinguished. The type of plywood shall denote first the quality of face followed by the quality of back. For example, Type AA shall have both surfaces of quality A, Type AB shall have face of quality A and the back of quality B and Type BB shall have both the surfaces of quality B.

5.2 The quality requirement of each of the surfaces mentioned under 5.1, shall conform to the

requirements given in Table 1. However, the maximum number of categories of defects permitted on any one surface of the panel shall be restricted in accordance with the requirements laid down in Table 2.

6 MATERIALS

6.1 Timber

Any species of timber may be used for plywood manufacture. However, a list of species, for the manufacture of plywood is given in Annex B for guidance.

6.2 Adhesive

The adhesive used for bonding the veneers in different grades of plywood shall be the corresponding type of adhesive as specified in IS 848 : 1974.

6.2.1 Extenders conforming to IS 1508 : 1972 may be used with the synthetic resin adhesive (aminoresins). However, synthetic resin adhesives (aminoresin) when extended by more than 25 percent shall contain suitable preservative chemicals in sufficient concentration to satisfy the mycological test described in 11.2.2.

7 MANUFACTURE

7.1 The veneers for all the grades shall be either rotary cut or sliced. The veneers shall be sufficiently smooth to permit an even spread of adhesive. Treatment as specified below shall be given to the plywood either at the veneer stage or after converting the veneers into boards.

7.1.1 Treatment

Veneers from non-durable species and sapwood of all species when used for plywood manufacture shall be soaked in 1.25 percent solution of boric acid or 1.9 percent solution of borax at a temperature of 85-90°C for a period of 10-40 minutes depending upon the thickness of the veneers or the veneers may be dipped in 2 percent solution of boric acid or 3 percent borax solution for 2 minutes and block stacked at least for two hours. Alternatively, the veneers may be soaked at an ambient temperature in a mixture of 0.5 percent solution

Table 1 Quality Requirements of Plywood for General Purposes

(Clause 5.2)

Sl No.	Defect Categories	Types of Surfaces	
		A	B
(1)	(2)	(3)	(4)
i)	Blister	Nil	Nil
ii)	Checks	Individual check not more than 50 mm in length and the total length not more than 300 mm/m ²	Individual check not more than 100 mm in length and the total length not more than 1 000 mm/m ²
iii)	Discoloration	Nil	5 percent
iv)	Dote	5 cm/m ²	15 cm/m ²
v)	Insect hole	Scattered up to 12 holes/m ²	Scattered up to 24 holes/m ²
vi)	Joints	One joint for every multiple of 200 mm provided no individual piece is less than 100 mm in width	No restriction
vii)	Knots (dead)	2 up to 12 mm dia/m ²	4 up to 20 mm dia/m ²
viii)	Pin knots (dead)	2/m ²	6/m ²
ix)	Pin knots (Live)	No restriction	No restriction
x)	Knots (tight)	6 up to 25 mm dia/m ²	No restriction
xi)	Patches	4 patches/m ² provided they are all tight patches and do not mar the appearance	Any number provided they are all tight patches and do not mar the appearance
xii)	Splits	2 splits, each not more than 1 mm wide and length not more than 100 mm provided they are filled with suitable filler	3 splits, each not more than 4 mm wide and length not more than 150 mm provided they are filled with suitable veneer inserts. Splits up to 25 mm long and 0.8 mm wide may be ignored provided they are suitably filled with a filler
xiii)	Swirl	Unlimited, provided they do not mar the appearance	No restriction

of sodium pentachlorophenate (Na PCP) and 1.5 percent of borax in water, for a period of 2 minutes and then stacked for at least half an hour before drying.

Table 2 Permissible Categories of Defects

(Clause 5.2)

Type of Surface	Maximum Number of Categories of Permissible Defects per sq metre
A	3
B	5

For BWR grade of plywood bonded with synthetic resin adhesive, the preservative may be given conveniently after boards come out of the press, while still hot or the treatment given to the veneers before bonding.

For BWR grade, fixed type of preservative may be used subject to the agreement between the manufacturer and the user according to IS 5539 : 1966.

7.2 Assembly

7.2.1 Thickness

The thickness of all veneers shall be uniform within a tolerance of ± 5 percent. Corresponding veneers on either side of the central ply and those of face and back veneers shall be of species having similar physical and mechanical properties, such as, density, modulus of elasticity, shrinkage, etc. to ensure balanced construction.

7.2.2 Joints in Veneers

Veneers that require to be joined to form a ply shall be spliced (edge jointed) before assembly. All joints shall be cut square. They may be taped on the face of the outer veneers in which case the tape shall be removed at a later stage, and metal clips or staples, if used, shall be removed. Perforated tapes may be used on the glue side of the veneers. In assembly, joints in veneers running in the same direction shall be staggered. End joints and butt joints shall not be permitted for any of the surfaces.

7.2.3 Grain Direction

Unless otherwise specified by the purchaser and except in boards comprising an even number of plies, the direction of grain of the veneer in adjacent plies shall be at right angles to each other, and that of the outer plies shall run parallel to the longer side of the board. In boards comprising even number of plies, the grain of the centre pair shall follow the same direction. In adjacent plies, the grain should be at right angles to each other. However, a deviation not exceeding 10° may be permitted. In all cases, the grain on both faces of the assembly boards shall run in the same direction.

7.2.4 Scarf Joints

When sizes larger than the available press sizes are required, scarf joints through the thickness of the board are permitted. All scarf joints shall be bonded with the same or a better adhesive than the one used for the manufacture of plywood, and shall be made with an inclination not greater than 1 in 12.

7.2.5 Permissible Defects

7.2.5.1 Gaps in cores and cross-bands may be permitted except for 3 ply plywood provided the width of the gap does not exceed 1 mm in case of and 2 mm in case of plywood of more than 5 ply and provided such gaps, if more than one, shall be spaced not less than 80 mm away from each other and are staggered not less than 50 mm away as between ply, the next ply having the same grain direction.

7.2.5.2 Splits in cores and cross-bands may be permitted to an extent of 2 per core or cross-band.

7.2.5.3 Overlap shall not be permitted.

8 DIMENSIONS AND TOLERANCES

8.1 The dimensions of plywood boards shall be as given in IS 12049 : 1987.

NOTE — Any other dimension as agreed to between the manufacturer and the purchaser may be used.

8.2 Thickness

Unless otherwise specified, thickness of plywood boards shall be as specified in Table 3. The thickness shall be measured up to one place of decimal.

8.3 Tolerances

The following tolerances on the nominal sizes of finished boards shall be permissible:

<i>Dimension</i>	<i>Tolerance</i>
a) Length	: + 6 mm - 0 mm
b) Width	: + 3 mm - 0 mm
c) Thickness	
1) less than 6 mm	: ± 10%
2) 6 mm and above	: ± 5%
d) Squareness	: 0.2%
e) Edge straightness	: 0.2%

Table 3 Thickness of Plywood Boards
(Clause 8.2)

Board	Thickness mm	Board	Thickness mm
(1)	(2)	(1)	(2)
3 ply	3, 4, 5, 6	9 ply	12, 15, 16, 19
5 ply	5, 6, 8, 9	11 ply	19, 22, 25
7 ply	9, 12, 15, 16	Above 11 ply	As ordered

9 WORKMANSHIP AND FINISH

9.1 The plywood boards shall be of uniform thickness within the tolerance limits specified under 8.3.

9.2 The faces of plywood boards shall be reasonably smooth and face veneers shall be of reasonably uniform thickness. Slight sanding may be given to rough boards in order to make them reasonably smooth. The squareness and edge straightness of the board when measured according to the procedure given in Annex C shall be as given in 8.3.

10 SAMPLING

10.1 The method of drawing representative samples and the criteria for conformity shall be as prescribed in IS 7638 : 1975.

11 TESTS

11.1 Six test pieces, cut from each of the boards selected under 10.1 shall be subjected to the tests specified in 11.2 and 11.3.

11.2 Glue Adhesion

Glue adhesion shall be deemed satisfactory if the plywood complies with the requirements specified in 11.2.1, 11.2.2 and 11.2.3.

11.2.1 Glue Shear Strength in Dry State

The plywood when tested in accordance with IS 1734 (Part 4) : 1983 shall have an average and a minimum individual shear strength not less than the values specified in Table 4 against each grade.

11.2.2 Mycological Test

The plywood when tested in accordance with IS 1734 (Part 7) : 1983 shall have an average and a minimum individual shear strength, not less than the values shown in Table 4 against each grade.

11.2.3 Water Resistance Test

The plywood when tested in accordance with IS 1734 (Part 6) : 1983 shall have an average and a minimum individual shear strength, not less than the values shown in Table 4 against each grade.

11.3 Moisture Content

The plywood when tested in accordance with IS 1734 (Part 1) : 1983 shall have a moisture content not less than 5 percent and not more than 15 percent.

11.4 For the purpose of tests specified in 11.2 and 11.3, the mean of all the observations and the minimum individual value of the observations shall be reported in the form given in Annex D.

Table 4 Average and Minimum Individual Shear Strength for Plywood
(Clauses 11.2.1, 11.2.2 and 11.2.3)

Sl No.	Grade	Shear Strength, Min (N)		
		Dry State (3)	Mycological (4)	Water Resistance (5)
(1)	(2)			
i)	BWR			
	Minimum Average	1 350	1 000	1 000
	individual	1 100	800	800
ii)	MR			
	Minimum Average	1 000	800	800
	individual	800	650	650

11.5 Retest

If the samples selected as specified in 10.1 are

found not to be fully complying with the requirements of 11.2 and 11.3, a further similar set of samples shall be taken at random from the same batch and subjected to the tests. If any of the samples in the second set is also found not to comply fully with the requirements of test, all the boards in the batch represented by the samples shall be rejected.

11.6 Other Tests

For testing any other mechanical property of general purpose plywood, subject to agreement between the purchaser and the supplier, reference shall be made to the provisions of IS 1734 (Parts 1 to 20) : 1983.

12 MARKING

12.2 Each plywood board shall be legibly and indelibly marked or stamped with the following:

- Indication of the source of manufacture,
- Year of manufacture,
- Batch No., and
- The grade and type as follows:
BWR/AA, BWR/AB, BWR/BB,
MR/AA, MR/AB, MR/BB

12.2 All markings shall be done on the face of the board near one corner.

13 DELIVERY

13.1 Unless otherwise specified, the plywood boards shall be delivered in a clean condition and shall be suitably packed according to normal trade.

ANNEX A

(Clause 2.1)

LIST OF INDIAN STANDARDS REFERRED IN THIS STANDARD

IS No.	Title	IS No.	Title
707 : 1976	Glossary of terms applicable to timber and timber products (second revision)	1734 (Part 4) : 1983	Methods of test for plywood : Part 4 Determination of glue shear strength (second revision)
848 : 1974	Specification for synthetic resin adhesives for plywood (phenolic and aminoplastic) (first revision)	1734 (Part 6) : 1983	Methods of test for plywood : Determination of water resistance
1508 : 1972	Specification for extenders for use in synthetic resin adhesive (urea-formaldehyde) for plywood (first revision)	1734 (Part 7) : 1983	Methods of test for plywood : Part 7 Mycological test (second revision)
1734 (Part 1) : 1983	Methods of test for plywood : Part 1 Determination of density and moisture (second revision)	7638 : 1975	Methods of sampling of plywood
		12049 : 1987	Dimension and tolerances relating to wood based panel materials

ANNEX B

(Clause 6.1)

TIMBER SPECIES OF PLYWOOD

NOTE — Species of timber to be treated (see 71.1) are indicated by dagger (†).

Sl No.	Trade Name	Botanical Name	Abbreviation	Sl No.	Trade Name	Botanical Name	Abbreviation
1.	Aini	<i>Artocarpus hirsutus</i>	AIN	33.	Indian Oak	<i>Quercus semecarpifolia</i>	IOA
2.	†Alder	<i>Alnus nitida</i>	ALD	34.	Indian Oak	<i>Quercus dilatata</i>	IOA
3.	†Alder	<i>Alnus</i> spp.	ALD	35.	Indian Oak	<i>Quercus serrata</i>	IOA
4.	Amari	<i>Amoora</i> spp.	AMA	36.	Jaman	<i>Syzygium</i> spp.	JAM
5.	†Amra	<i>Spondias</i> spp.	AMR	37.	†Jhingan	<i>Lannea coromandelica</i> (Syn: <i>Lannea grandis</i>)	JHI
6.	Arjun	<i>Terminalia arjuna</i>	ARJ	38.	Jutili	<i>Altingia excelsa</i>	JUT
7.	†Bahera	<i>Terminalia bellerica</i>	BAH	39.	†Kadam	<i>Anthocephalus cadamba</i>	KAD
8.	†Banati	<i>Lophopetalum wightianum</i>	BAN	40.	†Kanju	<i>Holoptelea integrifolia</i>	KAN
9.	†Birch	<i>Betula</i> , spp.	BIR	41.	†Karani	<i>Cullenia rosayroana</i> (Syn. <i>cullenia excelsa</i>)	KAR
10.	Bonsum	<i>Phoebe</i> spp.	BON	42.	Kathal	<i>Artocarpus heterophyllus</i>	KAT
11.	†Carallia	<i>Carallia brachiata</i> (Syn. <i>Carallia integerrima</i>)	CAR	43.	Kindal	<i>Terminalia paniculata</i>	KIN
12.	Champ	<i>Michelia</i> spp.	CHM	44.	Kokko	<i>Albizia lebbeck</i>	KOK
13.	Chaplash	<i>Artocarpus Chaplasha</i>	CHP	45.	†Lampati	<i>Duabanga grandiflora</i>	LAP
14.	†Chatian	<i>Alstonia scholaris</i>	CHT	46.	Laurel	<i>Terminalia tomentosa</i>	LAU
15.	Chikrassy	<i>Chukrasia tabularis</i>	CHI	47.	†Litsa	<i>Liteasa polyantha</i>	LIT
16.	†Chilauni	<i>Schima wallichii</i>	CHL	48.	†Machilus	<i>Machilus</i> spp.	MAC
17.	Cinnamon	<i>Cinnamomum cecicodaphne</i>	CIN	49.	Mahogany	<i>Swietenia</i> spp.	MAG
18.	†Debdaru	<i>Polyalthia</i> spp.	DEB	50.	†Maina	<i>Teterameles nudiflora</i>	MAI
19.	†Dhup	<i>Canarium</i> spp.	DHU	51.	Makai	<i>Shorea assamica</i>	MAK
20.	†Didu	<i>Salmalia insignis</i>	DID	52.	†Mango	<i>Mangifera indica</i>	MAN
21.	†Dillenia	<i>Dillenia</i> spp.	DIL	53.	Maple	<i>Acer</i> spp.	MAP
22.	Ebony	<i>Diospyros</i> spp.	EBO	54.	Menudito	<i>Enterolobium</i> spp. (Exotic)	MEN (ENT)
23.	Elm	<i>Ulmus wallichiana</i>	ELM	55.	Mullilam	<i>Fagara budrunga</i> (Syn. <i>Zanthoxylum rhetsa</i>)	MUI
24.	Gamari	<i>Gmelina arborea</i>	GAM	56.	†Mundani	<i>Acrocarpus fraxinifolius</i>	MUN
25.	†Garuga	<i>Garuga pinnata</i>	GAU	57.	†Narikel	<i>Pterygota alata</i>	NAR
26.	†Gokul	<i>Ailanthus grandis</i>	GOK				
27.	Gurjan	<i>Dipterocarpus</i> spp.	GUR				
28.	†Gutel	<i>Trewia nudiflora</i>	GUT				
29.	Haldu	<i>Adina cordifolia</i>	HAL				
30.	Hathipaila	<i>Pterospermum acerifolium</i>	HAT				
31.	†Hollock	<i>Terminalia myriocarpa</i>	HOL				
32.	Hollong	<i>Dipterocarpus macrocarpus</i>	HON				

Sl No.	Trade Name	Botanical Name	Abbreviation	Sl No.	Trade Name	Botanical Name	Abbreviation
58.	Neem	<i>Azadirachta indica</i>	NEE	72.	Rosewood	<i>Dalbergia latifolia</i>	ROS
59.	Nodunari	<i>Mansonia</i> spp.	NED	73.	†Salai	<i>Boswellia serrata</i>	SAA
60.	Pali	<i>Paiaquium ellipticum</i>	PAL	74.	Satinwood	<i>Chloroxylon swietenia</i>	SAT
61.	Persian Lilach	<i>Melia azadarach</i>	PLI	75.	Seleng	<i>Sapium baccatum</i>	SEL
62.	†Piney	<i>Kingiodendron pinnatum</i> (Syn. <i>Hardwickia pinnata</i>)	PIN	76.	†Semul	<i>Salmolia malabrica</i>	SEM
63.	Pitraj	<i>Aphanamixis polystachya</i>	PIT	77.	†Silver Oak	<i>Grevillea robusta</i>	SOA
64.	Poon	<i>Colopyllum</i> spp.	POO	78.	Sissoo	<i>Dalbergia sissoo</i>	SIS
65.	Poplar	<i>Populus ciliata</i>	POP	79.	Teak	<i>Tectona grandis</i>	TEA
66.	Poplar	<i>Populus deltoides</i>	POP	80.	Toon	<i>Cedrela</i> spp.	TOO
67.	†Pula	<i>Kydia calycina</i>	PUL	81.	†Udal	<i>Firmiana villosa</i> (Syn. <i>Sterculia villosa</i>)	UDA
68.	Pussur	<i>Xylocarpus molluccensis</i>	PUS	82.	Uriam	<i>Bischofia javanica</i>	URI
69.	Pyinma	<i>Lagerstroemia hypoleuca</i>	PYI	83.	†Vellapine	<i>Vateria Indica</i>	VEL
70.	Red Bombwe	<i>Planchonia valida</i> (Syn. <i>Planchonia andamanica</i>)	RBO	84.	†Walnut	<i>Juglans</i> spp.	WAL
71.	†Red Dhup	<i>Parishia insignis</i>	RDH	85.	†White Bombwe (badam)	<i>Terminalia procera</i>	WBO
				86.	White Cedar	<i>Dysoxylum malabricum</i>	WCE
				87.	†White Chuglam	<i>Terminalia bialata</i> (Sapwood)	WCH

ANNEX C

(Clause 9.2)

METHOD OF TEST FOR SQUARENESS AND EDGE STRAIGHTNESS

C-1 PROCEDURE FOR EDGE STRAIGHTNESS

C-1.1 The straightness of the edges and ends of plywood shall be verified against a straightedge not less than the full length of the plywood. If the edge on the end of plywood is convex, it shall be held against the straightedge in such a way as to give approximately equal gap at each end. The

largest gap between the straightedge and the edge shall be measured to the nearest millimetre and record.

C-2 PROCEDURE FOR SQUARENESS

C-2.1 The squareness of plywood shall be checked with a 1200 mm × 1200 mm square, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.

ANNEX D

(Clause 11.4)

FORM OF REPORT FOR TESTS ON PLYWOOD

1. Indication of the source of manufacture.....
2. Species used.....
3. Sizes of plywood boards.....
4. Thickness of plywood in mm:
 - a) Nominal.....
 - b) Actual average.....
5. No. of veneers in plywood.....
6. Glue shear strength in dry state as determined by the method given in IS 1734 (Part 4) : 1983

	Average.....
	Individual.....
7. Results of shear strength after mycological test as determined by the methods given in IS 1734 (Part 7) : 1983

	Average.....
	Individual.....
8. Results of moisture resistance test as determined by the method given in IS 1734 (Part 6) : 1983

	Average.....
	Individual.....
9. Average moisture content of plywood as determined by the method given in IS 1734 (Part 1) : 1983
10. Details of defects of face and back

	Face.....
	Back.....
11. General remarks on compliance with the specification.....
12. Certified that:
 - *The plywood passed the requirements..... Grade.....
 - Type.....of plywood according to IS :.....in all respects.
 - *The plywood failed to conform to IS :.....for reasons given in Sl. No. above.

Signature of Testing Officer.....

Designation.....

Name of Testing Laboratory.....

*Source out either remark.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc : No. CED 20 (4395)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all Offices)

Regional Offices :

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone
{ 331 01 31
{ 331 13 75

Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola
CALCUTTA 700054

37 86 62

Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036

2 18 43

Southern : C. I. T. Campus, IV Cross Road, MADRAS 600113

41 29 16

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
BOMBAY 400093

6 32 92 95

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE.
FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR.
PATNA. TRIVANDRUM.

AMENDMENT NO. 1 NOVEMBER 1992
TO
IS 303 : 1989 PLYWOOD FOR GENERAL PURPOSES —
SPECIFICATION

(Third Revision)

(Foreword, para 4, line 1) — Substitute 'BWP' for 'BWR'.

(Page 1, clause 6.2.1, lines 3 and 4) — Substitute 'synthetic resin adhesive (aminoresins)' for 'synthetic resin adhesives (aminoresin)'.

(Page 2, clause 7.1.1, last sentence) — Substitute 'IS 5539 : 1969' for 'IS 5539 : 1966'.

(Page 2, clause 7.2.1, line 6) — Substitute 'elasticity' for 'electricity'.

(Page 3, clause 7.2.5.1) — Insert ',' after the word 'plywood' in line 2 and insert '5 ply' after the words 'in case of' in line 3.

(Page 4, Annex A) — Substitute the following for the existing titles for 'IS 707 : 1976 ' and IS 1734 (Part 1) : 1983':

a) 'IS 707 : 1976 Glossary of terms applicable to timber technology and utilization (*second revision*)

IS 1734 (Part 1) : 1983 Methods of test for plywood: Part 1 Determination of density and moisture content (*second revision*)'

b) Insert the following in the list:

'IS 5539 : 1969 Specification for preservative treated plywood:

(Page 5, Annex B, Note) — Substitute '7.1.1' for '71.1'.

(Page 6, Annex B, Sl No. 76) — Substitute '*Salmalia malabarica*' for '*Salmolia malabrca*'.

(CED 20)

AMENDMENT NO. 2 MARCH 2000
TO
IS 303 : 1989 PLYWOOD FOR GENERAL PURPOSES
— SPECIFICATION

(Third Revision)

(Second cover page, Foreword) — Insert the following after fifth para as a separate para:

‘A scheme of labelling environment friendly products to be known as ECO Mark has been introduced at the instance of the Ministry of Environment and Forests (MEF), Government of India. The ECO Mark shall be administered by the *Bureau of Indian Standards (BIS)* under the *BIS Act, 1986* as per the Resolution No. 71 dated 21 February 1991 and Resolution No. 425 dated 28 October 1992 published in the Gazette of the Government of India. For a product to be eligible for ECO Mark, it shall also carry the Standard Mark of the BIS besides meeting additional environment friendly requirements. For this purpose, the Standard Mark of BIS would be a single mark being a combination of the ISI Mark and the Eco logo. Requirements to be satisfied for a product to qualify for the BIS Standard Mark for Eco friendliness, will be included in the relevant published Indian Standards through an amendment. These requirements will be optional; manufacturing units will be free to opt for ISI Mark alone also.

The amendment pertaining to Eco criteria is based on the Gazette Notification No. 170 dated 18 May 1996 for Wood Substitutes as Environment Friendly Products published in the Gazette of the Government of India.’

(Page 1, clause 6.1) — Insert the following at the end of the clause:

‘For ECO Mark only species of wood from sources other than natural forests such as wood from rubber, coconut, cashew, industrial and social forestry plantations etc and shade trees from tea and coffee estates shall be used for the manufacture of plywood.’

(Page 3, clause 10.1) — Substitute ‘IS 7638:1999’ for ‘IS 7638:1975’.

(Page 4, clause 11.6) — Insert the following new clause after 11.6 and renumber the subsequent clauses:

1.12 OPTIONAL REQUIREMENTS FOR ECO MARK

12.1 General Requirements

12.1.1 The plywood shall conform to the requirements of quality and performance as specified in this standard.

12.1.2 The manufacturer shall produce to BIS environmental consent clearance from the concerned State Pollution Control Board as per the provisions of the *Water (Prevention and Control of Pollution) Act, 1974* and the *Air (Prevention and Control of Pollution) Act, 1981* and the *Water (Prevention and Control of Pollution) Cess Act, 1977* alongwith the authorization, if required under the *Environment (Protection) Act, 1986*, while applying for ECO Mark appropriate with enforced rules and regulations of Forest Department.

12.2 Specific Requirements

The plywood shall conform to the specific requirements given for ECO Mark under relevant clauses of the standard.

NOTE — The manufacturer shall provide documentary evidence by way of certificate or declaration to Bureau of Indian Standards while applying for ECO Mark.'

(*Page 4, renumbered clause 13.1*) — Insert the following matter under the clause:

'e) The criteria for which the plywood has been labelled as ECO Mark.'

(*Page 4, renumbered clause 14.1*) — Insert the following at the end of the clause:

'For ECO Mark the material used for packaging of the plywood shall be recyclable, reusable or biodegradable.'

(*Page 4, Annex A*) — Substitute 'IS 7638:1999 Wood/Lignocellulosic based panel products — Methods of sampling (*second revision*)' for 'IS 7638 : 1975 Methods of sampling of plywood'.

(CED 20)

AMENDMENT NO. 3 DECEMBER 2004
TO
IS 303 : 1989 PLYWOOD FOR
GENERAL PURPOSES — SPECIFICATION

(Third Revision)

(Page 1, clause 6.2.1, first sentence) — Substitute the following for the existing:

‘Extenders may be used with the synthetic resin adhesive (aminoresins).’

(Page 3, clause 8.1) — Substitute the following for the existing clause:

8.1 The dimensions of plywood boards shall be as follows:

2 400 mm × 1200 mm 2 100 mm × 900 mm

2 100 mm × 1200 mm 1 800 mm × 900 mm

1 800 mm × 1200 mm

NOTE — Any other dimensions as agreed to between the manufacturer and the purchaser may also be used.’

(Page 4, Annex A) — Delete the following reference:

‘12049 : 1987 Dimension and tolerances relating to wood based panel materials’

(CED 20)

AMENDMENT NO. 4 AUGUST 2005
TO
IS 303 : 1989 PLYWOOD FOR GENERAL PURPOSES —
SPECIFICATION

(Third Revision)

(Page 3, clause 11.1, line 3) — Substitute '11.2, 11.3 and 11.4' for '11.2 and 11.3'.

(Page 3, clause 11.2) — Substitute the following for the existing:

'11.2 Glue Adhesion

Glue adhesion shall be deemed satisfactory if the plywood complies with the requirements specified in 11.2.1 and 11.2.2.

11.2.1 Water Resistance Test

Plywood for general purposes of either grade, when tested in the manner specified below shall satisfy minimum pass standard for test for adhesion of plies as given in IS 1734 (Part 5).

11.2.1.1 Three test specimens of size 250 mm × 100 mm shall be prepared from each of the boards selected under 10.1 and shall be tested for respective grade as described below.

BWR Grade

Specimens shall be submerged in boiling water for 8 h and dried for 16 h at a temperature of $65 \pm 2^{\circ}\text{C}$ and then followed by two more cycles of soaking and drying under the same conditions described above. The specimens shall then be tested in accordance with the method given in IS 1734 (Part 5).

MR Grade

Specimens shall be submerged in water at a temperature of $60 \pm 2^{\circ}\text{C}$ for 3 h and dried for 8 h at a temperature of $65 \pm 2^{\circ}\text{C}$ and then followed by two more cycles of soaking and drying under the same conditions described above. The specimens shall then be tested in accordance with the method given in IS 1734 (Part 5).

11.2.2 *Mycological Test*

Plywood of MR Grade when tested in accordance with the method given in IS 1734 (Part 7) shall satisfy minimum pass condition for test for adhesion of plies as given in IS 1784 (Part 5).'

(Page 4, Table 4) — Delete.

(Page 4, clause 11.3) — Insert the following new clause after 11.3 and renumber the subsequent clauses:

'11.4 **Static Bending Strength** — Plywood when tested in accordance with IS 1734 (Part 11) shall have an average and a minimum individual Modulus of Elasticity and Modulus of Rupture not less than the values specified in Table 4 against each grade.

Table 4 Average and Minimum Individual Values of Modulus of Elasticity (MOE) and Modulus of Rupture (MOR)

Sl No.	Grade	MOE (N/mm ²)		MOR (N/mm ²)	
		Average	Min. Ind.	Average	Min. Ind.
(1)	(2)	(3)	(4)	(5)	(6)
i)	BWR Grade				
	Along (direction parallel to the grain direction of the face veneer)	5 000	4 500	40	36
	Across (direction perpendicular to the grain direction of the face veneer)	2 500	2 200	20	18
ii)	MR Grade				
	Along (direction parallel to the grain direction of the face veneer)	4 000	3 600	30	27
	Across (direction perpendicular to the grain direction of the face veneer)	2 000	1 800	15	13

[Page 4, clause 11.4 (renumbered 11.5), lines 1 and 2] — Substitute '11.3 and 11.4' for '11.2 and 11.3'.

(Page 4, clause 11.5 (renumbered 11.6), line 3) — Substitute '11.2, 11.3 and 11.4' for '11.2 and 11.3'.

(Page 4, Annex A) — Delete references of 'IS 1734 (Part 4) : 1983' and 'IS 1734 (Part 6) : 1983' and add reference to the following, at appropriate places:

'IS 1734 (Part 5) : 1983	Methods of test for plywood : Part 5 Test for adhesion of plies (<i>second revision</i>)
IS 1734 (Part 11) : 1983	Methods of tests for plywood : Part 11 Determination of static bending strength (<i>second revision</i>)'

(Page 7, Annex D, SI No. 6) — Substitute the following for the existing, delete SI Nos. 7 & 8 and renumber SI No. 9 as SI No. 7:

Glue Adhesion	a) Water Resistance test as determined by clause 11.2.1 of IS 303	-----
	b) Mycological Test as determined by clause 11.2.2 of IS 303	-----

(Page 7, Annex D) — Insert the following after the renumbered SI No. 7 and renumber the subsequent SI Nos. accordingly:

8(a)	Modulus of Elasticity as determined by method given in IS 1734 (Part 11) : 1983	Average: ----- Min. Ind. -----
8(b)	Modulus of Rupture as determined by method given in IS 1734 (Part 11) : 1983	Average: ----- Min. Ind. -----

(CED 20)

**AMENDMENT NO. 5 SEPTEMBER 2006
TO
IS 303 : 1989 PLYWOOD FOR GENERAL
PURPOSES — SPECIFICATION**

(Third Revision)

[Page 4, clause 12, Title (see also Amendment No. 2)] – Substitute
'ADDITIONAL' for 'OPTIONAL'.

(CED 20)

**AMENDMENT NO. 6 AUGUST 2007
TO
IS 303 : 1989 PLYWOOD FOR GENERAL
PURPOSES — SPECIFICATION**

(Third Revision)

[Page 3, clause 11.2.1.1 (see also Amendment No. 4)] — Insert the following Note at the end of the clause:

NOTE — The cycles of drying or soaking can be made up of a number of shorter periods of drying or soaking. In such instances the specimen shall be kept in air at $27 \pm 2^{\circ}\text{C}$ in between the shorter periods constituting the drying cycle and be kept submerged in water at $27 \pm 2^{\circ}\text{C}$ in between the shorter periods constituting the soaking cycle.

[Page 3, clause 11.2.2 (see also Amendment No. 4)] — Substitute 'IS 1734 (Part 5)' for 'IS 1784 (Part 5)'.